



Superior Solutions



EMULROUT

Bituminous mixture for direct application

- Cold-bitumen base.
- Does not require mixing or heating.
- Compatible with asphalt and concrete.
- Excellent adhesion and plasticity.
- Hardens by compacting and air action.
- Dries quickly.
- Very good resistance to high and low temperature.
- Instant repair of hollows and potholes in roads, parking areas, pedestrian ways, courtyards, school yards, communications, playgrounds, garden paths.

USAGE

For direct application.

A. FOR HOLES OF LESS THAN 4 CM:

Sweep the dirt, dust and water off.

Fill the hole with an adequate volume, so that the hole is slightly overfilled, and ensure that it overlaps over all the edges.

After this, pack it in with the bottom of the shovel or using a compacting ram or run over it with a vehicle.

B. FOR HOLES THAT ARE LARGER THAN 4 CM:

Create a filling that consists of a layer of the agent of thickness 1 cm on the bottom and the sides of the hole. After this, fill the hole with compactable material (building debris, small-grained gravel), properly pack it in and finish with a 2-cm layer of the agent and ensure that it is slightly above the surface level to allow for compacting of the agent using the back of the shovel or a compacting ram or by running over it with vehicles.

CONDITIONS FOR USE


See usage instructions on the pack. Hermetically close a partly used-up container. In winter, do not use the agent on holes that have been contaminated by the road maintenance salt. Product storage: 6 months in a sealed pack in a room with a temperature of 15 - 25°C.

CHARACTERISTICS

Appearance: Black or red-coloured solid substance.

Density: approximately 2.18

Average consumption: for an average-sized pot-hole (diameter 25 cm and depth 2 cm) = 2 kg



All information in this document is based on our practical experience and/or laboratory tests. Due to the large spectrum of circumstances for usage and unpredictable human factors, we recommend that you always test our products before final usage. This technical data sheet has perhaps already been revised based on legislation, availability of the individual ingredients or newly acquired information. We can send you upon request the latest valid version, which is at the same time the sole valid version.

Version: 1561-0710